

FORM PTO-1390	U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371	ATTORNEY'S DOCKET NUMBER: BO 42383 U.S. APPL. NO. (known, see 37 CFR 1.51) 09/857788
INTERNATIONAL APPLICATION NO.: PCT/NL98/00712	INTERNATIONAL FILING DATE: 11 December 1998	PRIORITY DATE CLAIMED:
TITLE OF INVENTION: METHOD FOR PRODUCING A SUBSTRATE WITH UNIDIRECTIONAL CONDUCTIVITY AND DISPLAY DEVICE USING SUCH A SUBSTRATE IN AN ANISOTROPIC CONTACT LAYER		
APPLICANT(S) FOR DO/EO/US: Jacobus Christiaan Gerardus Maria RUITER, Erik Maarten TERLOUW, Georges HADZIOANNOU and Hendrik-Jan BROUWER		
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:		
1.	<input checked="" type="checkbox"/>	This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2.	<input type="checkbox"/>	This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3.	<input checked="" type="checkbox"/>	This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4.	<input checked="" type="checkbox"/>	A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5.	<input checked="" type="checkbox"/>	A copy of the International Application as filed (35 U.S.C. 371(c)(2))
	a. <input checked="" type="checkbox"/>	is transmitted herewith (required only if not transmitted by the International Bureau).
	b. <input type="checkbox"/>	has been transmitted by the International Bureau. (see attached copy of PCT/IB/308)
	c. <input type="checkbox"/>	is not required, as the application was filed in the United States Receiving Office (RO/US).
6.	<input type="checkbox"/>	A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7.	<input type="checkbox"/>	Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
	a. <input type="checkbox"/>	are transmitted herewith (required only if not transmitted by the International Bureau).
	b. <input type="checkbox"/>	have been transmitted by the International Bureau.
	c. <input type="checkbox"/>	have not been made; however, the time limit for making such amendments has NOT expired.
	d. <input type="checkbox"/>	have not been made and will not be made.
8.	<input type="checkbox"/>	A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9.	<input type="checkbox"/>	An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10.	<input type="checkbox"/>	A translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).
Item 11. to 16. below concern document(s) or information included:		
11.	<input type="checkbox"/>	An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12.	<input type="checkbox"/>	An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13.	<input type="checkbox"/>	A FIRST preliminary amendment.
14.	<input type="checkbox"/>	A SECOND or SUBSEQUENT preliminary amendment.
15.	<input type="checkbox"/>	A substitute specification.
16.	<input checked="" type="checkbox"/>	A change of power of attorney and/or address letter.
17.	<input checked="" type="checkbox"/>	Other items or information:
International Preliminary Examination Report (PCT/IPEA/409) International Search Report (PCT/ISA/210) Abstract of the Disclosure on a separate sheet Application Data Entry Sheet		

U.S. APPLICATION NO. (if known, see 37 CFR 1.51)

097857788

INTERNATIONAL APPLICATION NO.
PCT/NL98/00712ATTORNEY'S DOCKET NO.
BO 4238317. ☒ The following fees are submitted:**BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)):**

Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO

\$ 1,000.00

International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO

\$ 860.00

International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO

\$ 710.00

International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4)

\$ 690.00

International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4)

\$ 100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =

\$ 860.00

Surcharge of \$130.00 for furnishing the oath or declaration later than 30 months from the earliest claimed priority date (37 CFR 1.492(e)).

\$ 130.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	24 - 20 =	4	X \$18.00	\$ 72.00	
Independent claims	3 - 3 =	0	X \$80.00	\$	
MULTIPLE DEPENDENT CLAIMS(S) (if applicable)			+ \$270.00	\$	
TOTAL OF ABOVE CALCULATIONS =				\$ 1,062.00	
Reduction of 1/2 for filing by small entity, if applicable. Applicant claims Small Entity Status under 37 CFR 1.27. +				\$	
SUBTOTAL =				\$ 1,062.00	
Processing fee of \$130 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.49(f)).				\$	
TOTAL NATIONAL FEE =				\$ 1,062.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$	
TOTAL FEES ENCLOSED =				\$ 1,062.00	
				Amount to be refunded:	
				charged:	


- a. ☒ A check in the amount of \$ 1,062.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. **25-0120** in the amount of \$ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required by 37 CFR 1.16 and 1.17, or credit any overpayment to Deposit Account No. **25-0120**. A duplicate copy of this sheet is enclosed.

SEND ALL CORRESPONDENCE TO:

Customer No. 000466YOUNG & THOMPSON
745 South 23rd Street
2nd Floor
Arlington, VA 22202
(703) 521-2297 facsimile (703) 685-0573

June 11, 2001

By


 Benoît Castel
 Attorney for Applicants
 Registration No. 35,041

09/857788

381 00 00 00/TT 11 JUN 2001

ABSTRACT OF THE DISCLOSURE

A method of manufacturing a substantially planar substrate (1), formed of at least a first and a second material (3, 4) having substantially different conductivities, such that conductive channels (2) are formed substantially perpendicular to the substrate surfaces, and the conductivity perpendicular to the substrate surfaces, as measured over a predetermined area, is substantially larger than the conductivity parallel to the substrate surfaces, Furthermore, a display device (23) includes at least one substrate (1) manufactured according to the present method, an optically active layer (8; 24), and at least one control electrode (10), thereby enabling the provision of a local electrical field over the optically active layer (8; 24).

10
5
10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995
1000

ART 34 AMDT

WO 00/36649

Rec'd PCT/PTO 11 JUN 2001
EPO-BO

12. 12. 2000 09/857788
PCT/NL98/00712

amended page
1

(42)

METHOD FOR PRODUCING A SUBSTRATE WITH UNIDIRECTIONAL CONDUCTIVITY AND DISPLAY DEVICE
USING SUCH A SUBSTRATE IN AN ANISOTROPIC CONTACT LAYER

The present invention relates to a method of manufacturing a
5 substantially planar substrate with a predetermined substrate
thickness, having a first substrate surface and a second substrate
surface extending substantially in parallel to the first substrate
surface, and being formed of at least a first and a second material
having substantially different conductivities, such that conductive
10 channels are formed substantially perpendicular to the substrate
surfaces, and the conductivity perpendicular to the substrate
surfaces, as measured over a predetermined area, is substantially
larger than the conductivity parallel to the substrate surfaces. The
present invention further relates to display devices using the
15 substrate with unidirectional conductivity.

Manufacturing of such substrates with unidirectional conductivity
are e.g. known from PCT/NL98/00341, which has not yet been published,
from the same applicant as the present application, which is included
<-> herein by reference.

20 For certain applications, a further insulation layer is added to
the substrates with unidirectional conductivity during further
processing. These insulation layer are e.g. used in the manufacturing
of liquid crystal displays (LCD) to protect against a short-circuit
situation when conductors on either side of the LC layer are pressed
25 together. For proper functioning of an LCD, a very thin insulating
layer is required. The addition of such a very thin insulation layer
further complicates the manufacturing process of numerous applications
of the substrate with unidirectional conductivity, e.g. the
manufacturing of LCD's.

30 Therefore, the object of the present invention is to provide a
method for manufacturing substrates with unidirectional conductivity
characteristics, including a very thin insulation layer, which is more
simple and cost-effective than separately applying insulation layers.

This object is obtained by the method as described in the
35 preamble, in which the method further comprises the steps of:

- providing a layer of the first material with a predetermined
thickness, having a first surface forming the first substrate surface;

<-> see additional page 1a

AMENDED SHEET

American patent US-A-5 805 424 discloses a microelectronic assembly including Z-
5 axis conductive films. These polymer films comprise nanopores, which are filled by either
gold or another metal, such as in the form of metal fibrils. It further discloses that a porous
film may be manufactured by having particles pass through the entire thickness of the film
and chemically etching the damaged tracks to obtain the pores.

American patent US-A-5 123 849 discloses a conductive gel area array connector,
10 having cavities containing a conductive gel. Only when the connector is put under pressure, a
connecting path is formed by the conductive gel.

American patent US-A-4 608 129 discloses a polymer film with a conductive pattern,
containing an electrically conductive polymer. This polymer may be one of many substances,
of which some have optical properties.

15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194

WO 00/36649

PCT/NL98/00712

2

- forming cavities in the first material in a predetermined pattern across a second surface of the first material, in which the cavities extend in a direction substantially perpendicular to the first surface over a predetermined depth; and

- 5 - applying the second material on the second surface of the first material until the cavities are at least filled, thereby forming the second surface of the substrate.

The method according to the present invention has the advantage that a substrate with the required characteristics (unidirectional
10 conductivity, very thin insulation layer) can be manufactured simply, requiring only a few production steps which are well known in the art. The further handling of these substrates is also simpler than the handling of both substrates with unidirectional conductivity and insulating layers in the same production process.

- 15 In a further embodiment of the method according to the present invention, the first material is an insulating material with a thickness equal to the substrate thickness and the cavities are manufactured to extend to a depth smaller than the thickness of the first material. In this embodiment the very thin insulating planar
20 layer of the substrate is formed by the remaining material of the first layer after formation of the cavities.

In a still further embodiment of the method according to the present invention, the second material is an insulating material and the method further comprises the steps of:

- 25 - applying the first material on a supporting structure with a thickness of less than the substrate thickness;
 - manufacturing the cavities such that the depth of the cavities is equal to the thickness of the first material;
 - applying the second material until the substrate reaches the
30 predetermined thickness;
 - forming the substrate by removing the supporting structure.

In this embodiment, the insulating layer is formed by the application of the second material to an extent that not only the cavities are filled, but also a thin insulating layer is formed on top
35 of the substrate.

The present methods can also be used to manufacture substrates with optically active material, such as liquid crystal. By filling the cavities in an insulating layer with optically active material, or by

WO 00/36649

PCT/NL98/00712

3

forming columns of optically active material and subsequently filling the spaces in between with insulating material. substrates may be formed with a predetermined pattern of optically active cells. This method of manufacturing optically active substrates is both simple and renders a large degree of freedom in defining the shape of the individual optically active cells and the pattern of optically active cells.

In a preferred embodiment the cavities in the layer of a first material are provided by etching techniques. As an alternative, laser beam evaporation or laser beam cutting can be used to provide the cavities in the first material.

A further object of the invention is to provide a method for producing a substrate in a simple and cost effective manner, which substrate can be used to provide an electric field distribution on the first surface of the substrate by locally applying a voltage on the second surface of the substrate with a local maximum value directly opposite a the locally applied voltage and decreasing value with increasing distance from the local maximum. This object is obtained by the method of manufacturing a substantially planar substrate with a predetermined substrate thickness, having a first substrate surface and a second substrate surface extending substantially in parallel to the first substrate surface, characterised in that the method comprises the steps of:

- producing spheres of a first, conductive material;
- coating the spheres with a thin layer of a second, insulating material;
- providing an insulating polymer, and distributing the coated spheres homogeneously in the insulating polymer;
- producing the substrate from the polymer containing the spheres.

Although this substrate is not suited for applications requiring a strict unidirectional conductivity to control an optically active layer, it can be used for applications which require a less strictly defined resolution and sharpness of the unidirectional conductivity, e.g. applications of the substrate in display devices with large dimensions.

amended page

4

A still further object of the invention is to provide display devices using the substrate manufactured according to one of the embodiments of the present invention.

This object is obtained by a display device comprising at least a first substrate manufactured according the present invention and a layer of conductive material substantially parallel to the first substrate, the display device further comprising an optically active layer positioned between the first substrate and the conductive layer, and at least one control electrode electrically connected to a surface of the first substrate opposite the optically active layer, thereby enabling the provision of a local electrical field over the optically active layer.

As an alternative, a display device is provided in which the layer of conductive material ~~is formed by~~ ^{<->} a second substrate manufactured according to one of the methods according to the present invention. The display device is provided with a plurality of further control electrodes on a surface of the second substrate opposite the optically active layer.

According to an embodiment of the display device according to the present invention, the optically active layer comprises dipole spheres with semispheres of a first and second colour, respectively, which dipole spheres can be aligned by the local electrical field, such that the semispheres of the first or second colour are aligned in the same direction.

An alternative embodiment of the display device according to the present invention comprises a layer of microcontainers filled with charged particles, which particles are moveable by the local electrical field.

A further alternative embodiment of the display device according to the present invention comprises an optically active layer formed by an electrocapillary sheet with electrocapillaries, in which a polarized fluid is contained in the electrocapillaries, which fluid ~~can~~ ^{<->} be displaced under the influence of an electric field.

In a still further embodiment of the display device according to the present invention, the optically active layer comprises double-funnel shaped pixels comprising two funnels, in which narrow parts of the funnels are connected to each other, in which the pixels are filled with a fluid, containing electrically charged particles, which

< comprises >
<< is arranged to be >>

AMENDED SHEET

~~and~~ ^{<->} be displaced through the funnels under the influence of an electric field.

A further aspect of the present invention concerns a display device comprising a first and a second substrate manufactured according to one of the claims 1 through 10, in which the first and second substrate are positioned substantially parallel to each other, an optically active layer is positioned between the first and second substrate, and a number of conductors are provided on the outside surfaces of the first and second substrate, thereby enabling the provision of a local electrical field in the optically active layer, characterised in that the optically active layer comprises a number of pixels comprising at least one flexible member of a first colour, at least one expandable member comprising at least an electrically driven chemomechanical polymer gel, and a fluid, which expandable member is arranged to press the flexible member against the second substrate under the influence of the local electrical field. Because the flexible member can be pressed against the first or second substrate, it is possible to provide a display device with a high degree of colour saturation.

The present invention also refers to the use of an electrically driven chemomechanical polymer gel to alter optical properties of a device provided with a flexible optical member, e.g. a flexible polymer lens, of which the optical properties may be altered by electrically driven chemomechanical polymer gel provided on the perimeter of the flexible lens.

The present invention will now be described in more detail, referring to the accompanying drawings, in which:

Fig. 1 shows a cross-sectional view of a substrate manufactured according to a preferred embodiment of the present;

Fig. 2 shows a phase of the production of a substrate with unidirectional conductivity according to a preferred method;

Fig. 3 shows the electrical equivalent of one conductive column, the insulation layer and a liquid crystal layer, driven by an electrical source;

Fig. 4 shows an assembly of a substrate manufactured according to the present invention, provided on a first side of an LC layer, with the insulating side of the substrate contacting the LC layer;

<is arranged to>

WO 00/36649

PCT/NL98/00712

6

Fig. 5 shows an illustration of an alternative method for manufacturing the substrate according to an embodiment of the present invention;

Fig. 6 shows an alternative for the embodiment shown in Fig. 5;

5 Fig. 7 shows an LCD comprising a substrate with unidirectional conductivity and a substrate with optically active material;

Fig. 8 shows a cross sectional view of a substrate manufactured according to a further embodiment of the present invention;

10 Fig. 9 shows a cross sectional view of a sphere used in the manufacturing of a substrate as shown in Fig. 8;

Fig. 10 shows a schematic cross sectional view of a substrate as shown in Fig. 8 applied on top of an LC layer;

Fig. 11 shows a simplified electrical equivalent circuit for the assembly shown in Fig. 10;

15 Fig. 12 shows the electrical field distribution over the LC layer of Fig. 10 for variations in radius of the conductive spheres;

Fig. 13 shows the electrical field distribution over the LC layer of Fig. 10 for variations in the thickness of the insulation layer;

20 Fig. 14 shows a cross sectional view of a display device with a structure similar to the LCD shown in Fig. 4, in which the LC layer is replaced by an optically active layer;

Fig. 15 shows a cross sectional view of an alternative arrangement for the display device of Fig. 14;

25 Fig. 16 shows a cross sectional view of alternative arrangement of the display device of Fig. 15, using double funnel shaped pixels comprising a fluid with charged particles;

Fig. 17a and 17b show a cross sectional view of one pixel of a display device according to a further embodiment of the present invention, in deactivated and activated situation, respectively;

30 Fig. 18a and 18b show a cross sectional view of a pixel according to a further embodiment of the pixel shown in Fig. 17, in deactivated and activated situation, respectively; and

35 Fig. 19 a and 19b show a cross sectional view of an alternative embodiment of the pixel shown in Fig. 18, in deactivated and activated situation, respectively.

Fig. 1 shows a cross-sectional view of a substrate 1 manufactured according to a preferred embodiment of the present invention. The substrate 1 is a planar substrate, and comprises numerous conductive

WO 00/36649

PCT/NL98/00712

7

columns 2 embedded in an insulating material 3. Although it is preferred that the conductive columns 2 are distributed over the substrate 1 in a regular pattern, a regular pattern is not required to give the substrate 1 the required characteristics of unidirectional conductivity. The insulating material 3 is provided such that a thin insulating layer 7 is provided on top of each conductive column 2. The substrate 1 with unidirectional conductivity according to the present invention can be used in applications, in which no current is required to flow from a first surface of the substrate 1 to the opposite surface. For instance, the substrate 1 can be used in applications, in which an electrical field is used for control, as in controlling a liquid crystal layer.

Fig. 2 shows a phase in the production of a substrate 1 with unidirectional conductivity according to a preferred method. According to this preferred embodiment, a flat supporting structure 5 is provided, on which a foil from a first material 4, e.g. a conductive, UV sensitive material is produced. This can, e.g., be done by casting or spin coating the first material 4 onto the supporting structure 5. Following regular procedures, known per se, the first material 4 can be solidified, e.g. by thermal hardening or evaporation of solvents. The foil is subsequently exposed to UV radiation, using a mask 6 to provide a pattern on the foil. The unexposed parts of the foil can be removed by using suitable solvents. As a result, a pattern of the first material 4 corresponding to the mask will remain on the supporting structure 5, e.g. a regular pattern of conductive columns 2. According to the present invention, a second material 3, in this case an insulating material, is applied on top of the conductive columns 2. The insulating material will fill the spaces between the conducting columns 2, but according to the present invention, insulating material 3 is applied until a thin planar layer of the insulating material 3 is provided on top of the columns 2. After hardening the insulation material 3, the supporting structure 5 can be removed, resulting in the substrate 1.

Because one surface of the substrate consists of the insulation material 3, the substrate 1 has a certain rigidity enabling simple handling of the substrate 1, without the need for a supporting layer 5 during further processing of the substrate 1.

WO 00/36649

PCT/NL98/00712

8

The structure of the resulting substrate 1, as shown in Fig. 1, with conductive columns 2 extending perpendicularly from one surface of the substrate 1 almost to the other side of the substrate 1, with only a small insulating layer on the other side, is very well suited for application in liquid crystal displays (LCD). Fig. 3 shows the electrical equivalent of one conductive column 2, the insulation layer 7 and a liquid crystal layer 8, driven by an electrical source 9. The height of the conductive column 2 is indicated by D1, the thickness of the thin insulation layer 7 by D2 and the thickness of the LC layer 8 by D3. Calculations of the electrical field strength show that in the LC layer 8, the electrical field equals

$$D3/(D2+D3) * U,$$

provided that the dielectric constant of the LC layer 8 and the insulating material 4 of the thin insulation layer 7 are substantially equal. When the thickness D2 of the insulation layer 7 is small compared to the thickness D3 of the LC layer 8, substantially all of the electrical field is concentrated in the LC layer 8 (the electrical field in the conductive column 2 being zero), allowing effective control of the LC layer 8.

In Fig. 4 an assembly 14 is shown of a substrate 1 manufactured according to the present invention, provided on a first side of an LC layer 8, with the insulating side of the substrate 1 contacting the LC layer 8. On the other side of the substrate 1, a number of control electrodes 10 may be provided, electrically connected to one or more of the conducting columns 2 of the substrate 1. On the second side of the LC layer 8, a thin insulating layer 11 is applied, after which a conductive layer 12 is applied covering the thin insulating layer 11. Finally, an insulating layer 13 is applied to the top of the assembly 14 to provide protection for the layers of the assembly 14. With the assembly 14 shown in Fig. 4, the LC layer 8 can be controlled by providing a voltage to one of the control electrodes 10, forming an LC Display. At the position of the control electrode 10, the conductive columns 2, which are in electrical contact with the control electrode 10, will provide the voltage up to the thin insulation layer 7. When the conductive layer 12 is held at ground potential, the LC layer 8 will alter its light transmission characteristics in the area between these conductive columns 2 and the conductive layer 12.

WO 00/36649

PCT/NL98/00712

9

Preferably, the control electrode 10 is in electrical contact with a large number of conductive columns 2. The larger the number of conductive columns 2 per control electrode 10, the higher is the attainable resolution and the less vulnerable is the device for failing or missing conductive columns 2. This has the advantage that no alignment is required of the control electrodes 10 with respect to the other layers 1, 8 of the assembly. It also allows more margins as to the number of conductive columns 2 in the substrate 1 that actually conduct from the first surface to almost the second surface of the substrate 1. Finally, the distribution of the conductive columns may vary over the substrate 1, allowing more margins in the manufacturing of the substrate 1.

The presence of the thin insulation layers 7, 11 between the LC layer 8 and, respectively the substrate 1 and the planar conductive layer 12 prevents the possibility of short-circuit in case of pressure exerted on both sides of the LCD 14.

In an alternative embodiment of the method according to the present invention, the cavities are not provided by etching, but by laser beam evaporation. This method is illustrated in Fig. 5. Preferably, a first layer 15 of insulating material is provided, onto which a laser beam 17 can be focused. By controlling the intensity and duration of light pulses of the laser beam 17, the first material 15 can be evaporated to a predetermined depth of the layer, thereby forming cavities in the first material. When the material is evaporated in such a way, that a predetermined thickness of the first material 15 is left, the first layer remains self supporting, thereby obviating the need for a supporting structure or layer as in the embodiment described above. By filling the cavities with a conductive material 18, e.g. a conductive polymer, conductive columns 2 are formed extending from a first side of the substrate 1 to almost the opposite side of the substrate 1.

By using laser beam evaporation to provide the cavities in the first material 15, the steps of producing a suitable mask, exposing the first layer through the mask, developing the layer and etching the layer are no longer needed, resulting in a more simple and precise production method of the substrate 1.

The laser beam evaporation method can also be used to produce a substrate 1 in which the conductive columns 2 are formed extending

WO 00/36649

PCT/NL98/00712

10

completely from the first side to the second side of the substrate 1. This further embodiment of the present invention is shown diagrammatically in Fig. 6. For this embodiment of the present invention, the laser can be used as a laser beam cutter, locally
5 evaporating all material of the first layer 15. After this laser beam cutting step, a layer of first, insulating material results in a certain pattern, provided with through-holes in a predetermined pattern. These through-holes can be filled with a second, conductive material 18, e.g. a conductive polymer, resulting in the substrate 1
10 with unidirectional conductivity. Preferably, a supporting structure 5 is used to facilitate production of a flat first substrate surface.

In two further alternative embodiments, the second material 18 used to fill the cavities in the layer of first material 15 is an optically active material, such as a liquid crystal (LC) material.
15 Preferably, in these embodiments, the number of conductive columns 2 per square unit in the substrate 1 is smaller than the number provided in the embodiments to provide a unidirectional conductive substrate 1.

As a further alternative, the optically active material is a photochargeable material, which converts light impinging on the
20 photochargeable material into an electrical charge. An even further alternative uses photoconductive material, of which the resistance is locally reduced where light impinges.

By combining the substrate 1 with unidirectional conductivity and a substrate 1' with optically active material, it is very simple to
25 produce an LCD 14, as shown in Fig. 7. This figure also shows that it is preferred that the concentration of conductive columns 2 in the substrate 1 with unidirectional conductivity to be higher than the concentration of LC cells 2' in order to enable a proper control of the LCD by the associated control conductors 10. Both substrates 1, 1'
30 can be provided with or without an insulating surface, i.e. all substrates can be manufactured according to any of the embodiments described above, as the LC material of the LC cells 2' is sensitive to the electric field across it. The use of the substrate 1' with the LC cells 2' will lead to a more precise definition of the display field
35 associated with each control electrode 10, as compared to the LCD 14 shown in Fig. 4.

The LCD 14 manufactured as described with reference to any of the above mentioned embodiments shows a large degree of flexibility with

WO 00/36649

PCT/NL98/00712

11

respect to display size, shape and pattern. The control electrodes 10 can be applied at a later production stage. Only at the final stage when the LCD 14 is completed, the control electrodes 10 have to be applied, defining the eventual appearance and characteristics of the
5 LCD 14.

In a still further embodiment of the method according to the present invention, a substrate 1 with unidirectional conductivity is made with a structure as shown in Fig. 8. The substrate 1 is formed by
10 conductive spheres 20 suspended in an insulating material 3. This substrate 1 or foil can be used in applications, in which the resolution and sharpness of the unidirectional conductivity is less important, e.g. in larger scale applications. Also, this substrate 1 can not be utilised in applications requiring DC-conductance, but is well suited for applications in which an electrical field has to be
15 applied locally.

The first step of manufacturing the substrate 1 according to this embodiment is the manufacturing of small spheres 20 from a conductive material 21, preferably a conductive polymer. In order to prevent electrical short-circuit between individual spheres 20, the spheres 20
20 are coated with a thin layer of insulating material 22, as illustrated in Fig. 9. The thickness of the insulating layer 22 affects the characteristics of the substrate 1, as will be discussed below.

The spheres 20 with the insulating layer 22 are, preferably, distributed homogeneously in a liquid polymer. By applying
25 manufacturing processes specific to the liquid polymer used, a planar substrate 1 is formed, e.g. by casting, UV-hardening, thermal hardening or evaporating solvents.

The substrate 1 can be used e.g. as an interface layer to control an optically active layer, such as an LC layer 8, in a manner
30 comparable to the LCD-assembly 14 discussed above. Fig. 10 shows a simplified diagram of the structure of the substrate 1 manufactured according to this embodiment in combination with a liquid crystal layer 8. In this drawing, r is the thickness of the insulation layer 22 of each sphere 20, R is the radius of the sphere 20, D is the total
35 thickness of the substrate 1 and d is the thickness of the liquid crystal layer 8. Fig. 11 shows a simplified electrical equivalent circuit of the substrate 1 and the LC layer 8. When a voltage source 9 is used to drive the LC layer 8 with ground connected to the LC layer

WO 00/36649

PCT/NL98/00712

12

8 and the positive voltage connected to the top surface of the substrate 1, the voltage at various positions in the substrate 1 and over the LC layer 8 can be calculated, as well as the electrical field. The electrical field in the LC layer 8, which is important for controlling the optical characteristics of the LC layer 8, can be expressed as

$$D4/(D1+D2+D3+D4) * U,$$

provided that the dielectric constant of the LC layer 8 and the insulating material 4 of the thin insulation layer 7 are substantially equal. In this formula, $D4$ is equal to the thickness d of the LC layer 8, $D1$ is the distance between the top two spheres 20 in the substrate 1 (equal to $2r$), $D2$ is the distance between the middle and lower sphere 20 (equal to $2r$), and $D3$ is the distance between the lower sphere 20 and the top of the LC layer 8 (and equal to r). When $D4$ is large compared to $D1...D3$, i.e. when the LC layer 8 has a large thickness d compared to the thickness r of the sphere insulation 22, the major part of the electrical field will be concentrated in the LC layer 8, enabling an effective control of the display. In Fig. 11, M denotes the dimension of the conductive spheres 20, in which no electrical field is present.

Calculations with the simplified model described above, of the distribution of the electrical field over the LC-layer 8 in the assembly of substrate 1 and LC layer 8 as shown in Fig. 11 as a result of a voltage applied by an electrical source 9 have been made for variations of substrate thickness D , sphere radius R , insulation layer thickness r and thickness d of the LC layer 8. The measurement points are related to the thickness D of the substrate 1, in which the first measurement point is located directly opposite the electrical connection of the electrical source 9 to the substrate 1, and the next measurement points are located at distances equal to multiples of the substrate thickness D from the first measurement point. The results are shown in Fig. 12 for variations in radius R of the conductive spheres 20, and in Fig. 13 for variations in the thickness r of the insulation layer 22. The results show that the electrical field has a peak directly under the electrical connection of the electrical source 9 and rapidly decreases for the other measurement points. This substrate therefore can be used to locally apply an electric field, e.g. in an LCD.

WO 00/36649

PCT/NL98/00712

13

In Fig. 12, results of the electrical field distribution are shown for three different values of the sphere radius, with constant substrate thickness $D = 50 \mu\text{m}$, LC layer thickness $d = 2 \mu\text{m}$ and insulation layer thickness $r = 0.1 \mu\text{m}$. Line I shows the result for a sphere radius $R = 5 \mu\text{m}$, line II for $R = 2 \mu\text{m}$ and line III for $R = 0.5 \mu\text{m}$. The results show that a larger sphere radius R will lead to a higher local electrical field.

In Fig. 13, results of the electrical field distribution are shown for three different values of the insulation layer thickness r , with constant substrate thickness $D = 25 \mu\text{m}$, sphere radius $R = 0.5 \mu\text{m}$ and LC layer thickness $d = 2 \mu\text{m}$. Line I shows the result for insulation layer thickness $r = 0.1 \mu\text{m}$, line II for $r = 0.5 \mu\text{m}$ and line III for $r = 2 \mu\text{m}$. The results show that a larger insulation layer thickness r will lead to a lower local electrical field. Calculations for variations in substrate thickness D and LC layer thickness d show that a higher electric field is obtained for a larger LC-layer thickness d and for a smaller substrate thickness D . This is obvious, as the electrical field is distributed over the substrate 1 and the LC layer 8 according to their respective dielectric dimensions.

The substrate 1 manufactured according to this latter embodiment of the present invention can be used in applications in which the requirements with respect to the resolution and sharpness of the unidirectional conductivity may be less strict, e.g. applications of the substrate 1 in display devices with large dimensions.

As an alternative, the substrate manufactured according to this embodiment of the present method can be used as dielectric layer to produce capacitors with a large capacity.

Fig. 14 shows a cross sectional view of a display device 23 with a structure similar to the LCD 14 shown in Fig. 4, in which the LC layer 8 is replaced by an optically active layer 24. This display device may also be used as electric paper, as the different layers can be made very thin, resulting in a flexible paper-like display. The operation of the display device 23 is similar to the operation of the LCD 14, discussed with reference to Fig. 4. In Fig. 14, the optically active layer 24 is shown comprising numerous small dipole spheres 27. The optically active layer 24 comprising small dipole spheres 27 will be discussed in detail below.

WO 00/36649

PCT/NL98/00712

14

As an alternative, a display device 25 can be constructed as shown in Fig. 15. In this display device 25, the optically active layer 24 is sandwiched between two substrates 1, 1' according to the present invention, in which the insulating surfaces of the substrates 1, 1' are in contact with the optically active layer 24. On the other surfaces of the substrates 1, 1', a plurality of control electrodes 26, 26' can be electrically connected to the substrates 1, 1' in order to control the optical properties of the optically active layer 24. By applying a voltage between two control electrodes 26, 26' on each side of the display device 25, the optically active layer 24 is exposed to a local electrical field. In Fig. 15, the optically active layer 24 is shown comprising numerous microcontainers 29. The optically active layer 24 comprising microcontainers 29 will be discussed in detail below.

Similar to the optically active material used in an embodiment to manufacture the substrate 1 as already described above, the optically active layer 24 may consist of e.g. LC material, such that the electrical field applied is converted into optical transmission characteristics of the optically active layer 24. As an alternative, the optically active layer 24 may be provided as a layer of photochargeable material. In this case, the control electrodes 10, 26, 26' are used to pick up the electrical signal from the optically active material. In an even further alternative, the optically active layer 24 may be provided as a layer of photoconductive material, of which the resistance is reduced when light impinges on the display. This resistance change may be picked up by the control electrodes 10, 26, 26'.

In the embodiments shown in Fig. 14, the optically active layer 24 comprises small spheres, indicated by reference numeral 27, of which the two halves have a different colour. The spheres 27 are constructed as electrical dipoles. Because of the unidirectional conductive properties of the substrates 1, 1', an electrical field can be generated locally in the optically active layer 24 by applying a voltage on the control electrode 10 in the embodiment in Fig. 14 or between two control electrodes 26, 26' on both sides of the substrates 1, 1' in the embodiment shown in Fig. 15. Because of the dipole character of the small spheres 27, the spheres 27 will align with the local electrical field, enabling the formation of an image in the

WO 00/36649

PCT/NL98/00712

15

display device 23, 25. In an alternative embodiment, the small spheres 27 may be given a preferential direction. Applying an electric field in one direction will then cause the spheres 27 to align in one direction, while without an electrical field the spheres 27 will be aligned in another direction. The small spheres 27 and the optically active layer 24 may be manufactured according to the method published in European patent EP 0 540 281 of Xerox. Fabrication of a display device 23, 25 as described above is greatly simplified by using the substrates 1 with unidirectional conductivity according to the present invention.

In a further embodiment of the display device 23, 25 according to the present invention, the optically active layer 24, may comprise microcontainers 29 (dimensions in the order of ten microns) filled with a fluid of a first colour and charged particles with a second colour (dimensions in the order of microns). The microcontainers 29 may be comprised in the optically active layer 24 in a similar arrangement as the small spheres 27, as described above. Because of the electrostatic charge of the particles, the particles will move to one side of the microcontainer 29 under the influence of an electric field. When the particles have moved to one side of the microcontainer 29, their electrostatic charge will result in a new steady state because the particles will stay on the same place against the wall of the microcontainer 29. This enables to form a permanent image on the display device 23, 25, making it very suitable as electronic paper. As in the previous embodiment, the particles may be given a preferential position. Applying an electric field in one direction will then cause the particles to move to one side of the microcontainer 29, while without an electrical field the particles will remain in the other side. The operation and a manufacturing method for the microcontainers 29 and a layer containing microcontainers 29 is described in P. Drzaic et al., "A Printed and Rollable Bistable Electronic Display", SID 98 Digest, pp. 1131-1134.

In a further embodiment of a display device 23, 25 according to the present invention, the optically active layer 24 is formed by an electrocapillary sheet, containing numerous capillaries from one side of the sheet to the other, filled with a polar fluid. Under the influence of an electric field in the electrocapillary sheet, the fluid will move in a predetermined direction, thereby enabling the

WO 00/36649

PCT/NL98/00712

16

formation of an image on one side of the display device. The polar fluid may have different colours in separate capillaries to be able to form a coloured image. The electrocapillary sheet is described in e.g. EP-A-0 806 753 from Xerox.

5 In a fourth embodiment of the display device 23, 25 according to the present invention, the structure of the display device 23, 25 is again identical to the previous embodiments. In this embodiment, the optically active layer 24 is formed by a foil or plate provided with double funnel shaped pixels 28 perpendicular to the foil or plate, as
10 indicated in Fig. 16. The two funnels forming a pixel 28 are connected to each other at the small ends and are filled with a fluid. In the fluid electrically charged particles are dispersed. Under the influence of an applied local electrical field, the charged particles in the fluid are directed to one of the funnels of a pixel 28, thereby
15 allowing the formation of an image. The foil or plate with double funnel shaped pixels 28, forming the optically active layer 24, is described in European patent EP-0 783 163 from Xerox.

A fifth embodiment of the display device 23, 25 according to the present invention uses electrically driven chemomechanical polymer
20 gels. These polymer gels absorb or reject fluids when an electrical current flows through them and as a result the polymer gel will expand or diminish its volume. A cross sectional view of one pixel 30 of a plurality of pixels 30 forming a display device 23, 25 is shown in Fig. 17a and 17b. Examples of electrically driven chemomechanical gels
25 are described in Y. Osada et al., "A polymer gel with electrically driven motility", Nature, Vol. 355, no. 6357, pp 242-244, 16 January 1992.

More in general, electrically driven chemomechanical polymer gels can be used to alter the optical properties of a device provided with
30 a flexible optical member, e.g. a flexible lens, of which the optical properties may be altered by electrically driven chemomechanical polymer gel provided on the perimeter of the flexible lens.

In the fifth embodiment, for each pixel 30 of the display device 23, 25, a small sphere 31 made of flexible, conductive material is
35 positioned between and electrically connected to a first substrate 1 with conductive channels and a foil 32 coated with electrically driven chemomechanical polymer gel. The foil 32 coated with the gel is positioned a short distance from a second substrate 1' with conductive

WO 00/36649

PCT/NL98/00712

17

channels and a conductive fluid 33 is provided in the open space between the first substrate 1 and the second substrate 1'. On both the first substrate 1 and the second substrate 1', respective control electrodes 26, 26' are electrically connected. In this embodiment, an electrically driven chemomechanical polymer gel is used that rejects fluid when submitted to an electric current. The first situation, without an electrical current flowing through the pixel, is shown in Fig. 17a. When a current flows through the pixel 30, the electrically driven chemomechanical polymer gel rejects the fluid, causing the polymer gel to contract. Because only one side of the foil 32 is coated with the polymer gel, the foil will consequently bend, thereby pressing the flexible, conductive sphere 31 against the first substrate, as shown in Fig. 17b. When the fluid 33 has a first colour and the flexible conductive sphere 31 a second colour, the appearance of the pixel will change from the first colour to the second colour.

A further embodiment of the display device 23, 25 according to the present invention also uses an electrically driven chemomechanical polymer gel. Instead of a foil 32 coated with the electrically driven chemomechanical polymer gel, this embodiment uses cylinders 35 of electrically driven chemomechanical polymer gel in contact with the second substrate 1', as shown in Fig. 18a. In this embodiment, an electrically driven chemomechanical polymer gel is used that can absorb fluid 33 when a current flows through the pixel. Consequently, when a current is applied to the control electrodes 26, 26' of the pixel 30, the polymer gel cylinder 35 expands and presses the flexible conductive sphere 31 against the first substrate 1, as shown in Fig. 18b.

In a seventh embodiment of a display device according to the present invention, the flexible conductive spheres 31 of the sixth embodiment are replaced by a flexible conductive coating 37 on top of the polymer gel cylinder 35, as illustrated in a cross sectional schematic diagram in Fig. 19a and 19b. The operation of this embodiment corresponds to that of the sixth embodiment, as shown in Fig. 18a and 18b.

When the fluid 33 in the display device 23, 25 using the electrically driven chemomechanical polymer gel is an electrolytic fluid 3, it is possible to generate currents in the layer containing the pixels 30 by applying a voltage to the control electrodes 26, 26'.

WO 00/36649

PCT/NL98/00712

18

The currents are then generated by electron and ion movements in the electrolytic fluid 33 under the influence of the electrical field in the pixel 30. The electrically driven chemomechanical polymer gel will then expand or decrease under the influence of the induced current
5 until a steady situation is reached. In this case, it is possible to use substrates 1, 1', of which one surface consists entirely of insulating material 3.

By pressing a coloured flexible sphere 31 or coating 37 to the first substrate 1, the colour of the sphere 31 or coating 37 will
10 appear on the face of the display device 23, 25 with a high degree of colour saturation.

11 JUN 2001 09:48:00

WO 00/36649

PCT/NL98/00712

19

C l a i m s

1. Method of manufacturing a substantially planar substrate with a predetermined substrate thickness, having a first substrate surface
5 and a second substrate surface extending substantially in parallel to the first substrate surface, and being formed of at least a first and a second material having substantially different conductivities, such that conductive channels are formed substantially perpendicular to the substrate surfaces, and the conductivity perpendicular to the
10 substrate surfaces, as measured over a predetermined area, is substantially larger than the conductivity parallel to the substrate surfaces, characterised in that the method comprises the steps of:

- providing a layer of the first material (4; 15) with a predetermined thickness, having a first surface forming the first
15 substrate surface;

- forming cavities in the first material (4; 15) in a predetermined pattern across a second surface of the first material (4; 15), in which the cavities extend in a direction substantially perpendicular to the first surface over a predetermined depth; and

20 - applying the second material (3) on the second surface of the first material (4) until the cavities are at least filled, thereby forming the second surface of the substrate (1).

2. Method according to claim 1, characterised in that

25 - the first material is an insulating material (15) with a thickness equal to the substrate thickness;

- the cavities are manufactured to extend to a depth smaller than the thickness of the first material (15).

30 3. Method according to claim 2, characterised in that the second material is a conductive material (18).

4. Method according to claim 2, characterised in that the second material is an optically active material (18).

35 5. Method according to claim 1, characterised in that the second material is an insulating material (3) and the method further comprises the steps of:

- ~~applying the first material (4) on a supporting structure (5) with a thickness of less than the substrate thickness;~~
- ~~manufacturing the cavities such that the depth of the cavities is equal to the thickness of the first material (4);~~
- 5 - ~~applying the second material (3) until the substrate reaches the predetermined thickness;~~
- ~~forming the substrate (1) by removing the supporting structure (5).~~

10 6. Method according to claim 5, characterised in that the first material is a conductive material (4, 18).

7. Method according to claim 5, characterised in that the first material is an optically active material (4, 18).

15

8. Method according to one of the claims 5 through 7, characterised in that the first material (4) is UV sensitive and the method further comprises the steps of forming the cavities in the first material (4) by applying a mask (6) corresponding to the pattern

20 over the first material (4), exposing the first material (4) to UV radiation, and etching the first material (4).

9. Method according to one of the claims 1 through 7, characterised in that the cavities in the first material (15) are

25 formed by laser beam (17) evaporation.

10. Method of manufacturing a substantially planar substrate with a predetermined substrate thickness, having a first substrate surface and a second substrate surface extending substantially in parallel to

30 the first substrate surface, characterised in that the method comprises the steps of:

- producing spheres (20) of a first, conductive material (21);
- coating the spheres (20) with a thin layer (22) of a second, insulating material;
- 35 - providing an insulating polymer (3), and distributing the coated spheres (20) homogeneously in the insulating polymer (3);
- producing the substrate (1) from the polymer (3) containing the spheres (20).

~~such that the~~ ^{<resulting in an>} electric field distribution on the first surface of the substrate (1) ~~has~~ ^{<with>} a local maximum value directly opposite a locally applied voltage on the second surface of the substrate (1), which electrical field decreases with distance from the local maximum.

5

11. Display device (23) comprising at least a first substrate (1) manufactured according to one of the claims 1 through 10, and a layer of conductive material (12) substantially parallel to the first substrate (1), the display device (23) further comprising an optically active layer (8; 24) positioned between the first substrate (1) and the conductive layer (12), and at least one control electrode (10) electrically connected to a surface of the first substrate (1) opposite the optically active layer (24), thereby enabling the provision of a local electrical field over the optically active layer (8; 24).

15

12. Display device according to claim 11, characterised in that the layer of conductive material (12) ~~is formed by~~ ^{<comprises>} a second substrate (1'), also manufactured according to one of the claims 1 through 10, and in that the display device (25) is provided with a plurality of further control electrodes (10') on a surface of the second substrate (1') opposite the optically active layer (24).

20

13. Display device according to claim 11 or 12, characterised in that the optically active layer (24) comprises dipole spheres (27) with semispheres of a first and second colour, respectively, which dipole spheres (27) can be aligned by the local electrical field, such that the semispheres of the first or second colour are aligned in the same direction.

25

30

14. Display device according to claim 11 or 12, characterised in that the optically active layer (24) comprises microcontainers (29) containing charged particles, in which the charged particles are moveable to one side of the microcontainer (29) under the influence of the electric field.

35

amended page

22

15. Display device according to claim 14, characterised in that the microcontainers (29) comprise charged particles of one colour suspended in a fluid of a second colour.

5 16. Display device according to claim 14 or 15, characterised in that the charged particles are arranged to move to one side of the optically active layer (24) in the absence of an electrical field.

10 17. Display device according to claim 11 or 12, characterised in that the optically active layer (24) comprises an electrocapillary sheet with electrocapillaries, in which a polarized fluid is contained in the electrocapillaries, which fluid ~~can~~ ^{<->} be displaced under the influence of an electric field.

15 18. Display device according to claim 11 or 12, characterised in that the optically active layer (24) comprises double-funnel shaped pixels (28) comprising two funnels, in which narrow parts of the funnels are connected to each other, in which the pixels (28) are filled with a fluid, containing electrically charged particles, which
20 ~~can~~ ^{<->} be displaced through the funnels under the influence of an electric field.

25 19. Display device according to claim 18, characterised in that the charged particles have one colour and the fluid has a second colour.

30 20. Display device comprising a first and a second substrate manufactured according to one of the claims 1 through 10, in which the first and second substrate are positioned substantially parallel to each other, an optically active layer is positioned between the first and second substrate, and a number of conductors are provided on the outside surfaces of the first and second substrate, thereby enabling the provision of a local electrical field in the optically active layer, characterised in that the optically active layer (24) comprises
35 a number of pixels (30) comprising at least one flexible member (31, 37) of a first colour, at least one expandable member (32, 35) comprising at least an electrically driven chemomechanical polymer gel, and a fluid (33), which expandable member (32, 35) is arranged to

< is arranged to >

amended page
23

press the flexible member (31, 37) against the second substrate (1) under the influence of the local electrical field.

21. Display device according to claim 20, characterised in that

5 - the flexible members ~~are formed by~~ ^{<comprise>} a layer of flexible conductive spheres (31) arranged next to each other in electrical contact with the second substrate (1);

 - each expandable member comprises a foil (32) with a coating of electrically driven chemomechanical polymer gel on one side,
10 positioned such that the polymer coated side is in proximity of the first substrate (1') and the other side of the foil is in contact with at least one flexible conductive sphere (31);

 in which the polymer gel ~~will~~ ^{<is arranged to>} absorb the fluid (33) in the absence of an electrical field and ~~will~~ ^{<is arranged to>} discard the fluid (33) in the
15 presence of an electrical field, thereby bending the foil (32) and pressing the at least one flexible conductive sphere (31) against the second substrate (1).

22. Display device according to claim 20, characterised in that

20 - the flexible members ~~are formed by~~ ^{<comprise>} a layer of flexible conductive spheres (31) arranged next to each other in electrical contact with the second substrate (1);

 - the expandable members ~~are formed by~~ ^{<comprise>} flexible conductive polymer gel cylinders (35) in electrical contact with the first
25 substrate (1') and extending in the direction of the second substrate (1);

 - a conductive fluid (33) of a first colour is present between the cylinders (35) and the second substrate (1);

 in which the polymer gel cylinder (35) ~~will~~ ^{<is arranged to>} discard the fluid (33) in the absence of an electrical field and ~~will~~ ^{<is arranged to>} absorb the fluid (33) in the presence of an electrical field, thereby expanding and pressing the flexible conductive spheres (31) against the second
30 substrate (1).

35 23. Display device according to claim 20, characterised in that

 - the expandable members ~~are formed by~~ ^{<comprise>} flexible conductive polymer gel cylinders (35) in electrical contact with the first

substrate (1') and extending in the direction of the second substrate (1);

- a conductive fluid (33) of a second colour is present between the cylinders (35) and the second substrate (1);

- 5 - the flexible members ~~are formed by~~ ^{<comprise>} conductive coatings (37) of a second colour on top of each flexible conductive polymer gel cylinder (35);

- in which the polymer gel cylinder (35) ~~will~~ ^{<is arranged to>} discard the fluid (33) in the absence of an electrical field and ~~will~~ ^{<is arranged to>} absorb the fluid
10 (33) in the presence of an electrical field, thereby expanding and pressing the conductive coating (37) against the second substrate (1).

24. Use of an electrically driven chemomechanical polymer gel to alter optical properties of a device provided with a flexible optical
15 member.

09/857788

WO 00/36649

PCT/NL98/00712

1/5

Fig 1




Fig 2




Fig 3





Fig 4



09/857788

PCT/NL98/00712

WO 00/36649

2/5

Fig 5




Fig 6




Fig 7




Fig 8





Fig 9



09/857788

PCT/NL98/00712

WO 00/36649

3/5

Fig 10




Fig 11




Fig 12










Fig 13



4/5





Fig 14**Fig 15****Fig 16****Fig 17a****Fig 17b**

09/857788

PCT/NL98/00712

WO 00/36649

5/5

Fig 18a**Fig 18b****Fig 19a****Fig 19b**

COMBINED DECLARATION AND POWER OF ATTORNEY

(ORIGINAL DESIGN, NATIONAL STAGE OF PCT OR CIP APPLICATION)

As a below named inventor, I hereby declare that

My residence, post office address and citizenship are as stated below next to my name, I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Method for producing a substrate with unidirectional conductivity and display device using such a substrate

the specification of which: (complete (a), (b) or (c) for type of application)

REGULAR OR DESIGN APPLICATION

☐ is attached hereto.
☐ was filed on _____ as Application
Serial No. _____ and was amended on _____
(if applicable)

PCT FILED APPLICATION ENTERING NATIONAL STAGE

☐ was described and claimed in International application No. PCT/NL98/00712
filed on 11 December 1998
and as amended on _____ (if any)

ACKNOWLEDGEMENT OF REVIEW OF PAPERS AND DUTY OF CANDOR

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, paragraph 1.56(a).

In compliance with this duty there is attached an information
disclosure statement 37 CFR 1.97

PRIORITY CLAIM

I hereby claim foreign priority benefits under Title 35, United States Code paragraph 119 of any foreign application (s) for patent of inventor's certificate listed below and have also identified below any foreign application for patent of inventor's certificate having a filing date before that of the application on which priority is claimed.

(complete (d) or (e))

- d. ☐ no such applications have been filed
e. ☐ such applications have been filed as follows

**EARLIEST FOREIGN APPLICATION(S), IF ANY FILED WITHIN 12 MONTHS
(6 MONTHS FOR DESIGN) PRIOR TO SAID APPLICATION**

Country	Application Number	Date of filing (day, month, year)	Date of Issue (day, month, year)	Priority claimed
-	-	-	-	-

**ALL FOREIGN APPLICATION(S), IF ANY FILED MORE THAN 12 MONTHS
(6 MONTHS FOR DESIGN) PRIOR TO SAID APPLICATION**

CONTINUATION-IN-PART

(Complete this part only if this is a continuation-in-part application)

I hereby declare claim the benefit under Title 35, United States code, paragraph 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claim of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, paragraph 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, paragraph 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Application Serial No.) (Filing date) (Status) (patented, pending, abandoned)

(Application Serial No.) (Filing date) (Status) (patented, pending, abandoned)

POWER OF ATTORNEY

6 As a named inventor, I hereby appoint the following attorney(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: Robert J. PATCH, Reg. No. 17,355, Andrew J. PATCH, Reg. No. 32,925, Robert F. HARGEST, Reg. No. 25,590, Benoît CASTEL, Reg. No. 35,041, Eric Jensen, Reg. No. 37,855, and Thomas W. PERKINS, Reg. No. 33,027 c/o YOUNG & THOMPSON, Second Floor, 745 South 23rd Street, Arlington, Virginia 22202.

Address all telephone calls to Young & Thompson at 703/521-2297.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that wilful false statements and the like so made are punishable by fine or imprisonment, or both under Section 1001 of Title 18 of the United States Code and that such wilful false statements may jeopardize the validity of the application or any patent issued thereon.

1-00

Full name of sole or first inventor: RUITER, Jacobus Christiaan Gerardus Maria

Inventor's signature



Date 7 June 2001

Country of Citizenship: The Netherlands

NLX


Residence: ZOETERMEER, The Netherlands

Post Office Address: Shakespearezijde 22, NL-2725 NN Zoetermeer, The Netherlands

2-00

Full name of second inventor: TERLOUW, Erik Maarten

Inventor's signature



Date 7 June 2001

Country of Citizenship: The Netherlands

NLX

Residence: AMSTERDAM, The Netherlands

Post Office Address: Bloemgracht 109, NL-1016 KJ Amsterdam, The Netherlands

3-00

Full name of sole or first inventor: HADZIOANNOU, Georges

Inventor's signature:



Date 7 June 2001

Country of Citizenship: Greece

NLX


Residence: PEIZE, The Netherlands

Post Office Address: Boerakkerweg 3, NL-9321 EL Peize, The Netherlands

4-00

Full name of second inventor: BROUWER, Hendrik-Jan

Inventor's signature



Date 7 June 2001

Country of Citizenship: The Netherlands

NLX

Residence: GRONINGEN, The Netherlands

Post Office Address: Radijsstraat 2, NL-9741 BN Groningen, The Netherlands